

ANIONIC STABLE GRADE EMULSION (SANS 4001 BT-3)

PROPERTY	SS 60	TEST METHOD
1) Binder content, % (m/m)	60 - 62	SANS 4001 BT- 3 (5.2)
2) Residue on sieving, g/100 ml, Max.		
2.1) 710 µm	0.10	SANS 4001 BT- 3 (5.2)
2.2) 150 µm	0.25	SANS 4001 BT- 3 (5.2)
3) Sedimentation after 60 complete rotations	Nil	SANS 4001 BT-3 (5.6)
4) Coagulation value, % (m/m), max - Portland cement	2, Max	SANS 4001 BT- 3 (5.4)
5) Typical density at 25°C in kg / liter	1,000	ASTM D 3142 / D 3142 M-11
6) Uses	Slurry seals, Base Stabilisation, Fog-spray, Tack coats and Dust Palliatives	
7) Cleaning and handling	Refer Safety Data Sheets	

NOTE: This data is issued as a guide to the use of the product(s) concerned and whilst every effort is made to ensure the accuracy of the text which is in accordance with the latest technical developments, we cannot accept responsibility for any work carried out with our materials as we have no control over the method of application used or condition of site involved. In view of the constant research and development being undertaken in our laboratories we advise customers in their own interest to ensure that this data sheet has not been superseded by a more up-to-date publication. All products are sold subject to our standard conditions of sale which are available on demand.

Revised by: Larusha Gramni

Approved by: Johannes Lambert

Date: 30 September 2025